

# Information About *Molykote*<sup>®</sup> G-5008 Dielectric Grease

## Type

Silicone base oil containing specially formulated solid lubricants

## Physical Form

Light consistency grease

## Special Properties

Wide service temperature range; compatible with rubber and ceramics; excellent dielectric properties

## Primary Uses

Spark plug boots and electrical connectors

To reorder call:  
Polysi Technologies  
(T) 1-866-4-POLYSI  
(4-765974)  
(F) 1-919-775-2460

## DESCRIPTION

*Molykote*<sup>®</sup> G-5008 Dielectric Grease is a silicone grease containing a specially formulated base oil and solid lubricants. It has an NLGI 2-3 grade. It has excellent dielectric properties that are maintained when the material is exposed to temperatures above 200°C (392°F) for extended periods. It also inhibits bonding of rubber to ceramic.

## TYPICAL APPLICATIONS

*Molykote* G-5008 Dielectric Grease is designed primarily for rubber/ceramic and rubber/rubber applications such as automotive spark plug boots and electrical connectors.

## LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## TYPICAL PROPERTIES

**These values are not intended for use in preparing specifications.**

Color .....	Yellow-green
Penetration, unworked, mm/10, average.....	270
Apparent Viscosity, cSt.....	52,000
Bleed, 24 hours at 200°C (392°F), maximum percent .....	4.0
Evaporation, 24 hours at 200°C (392°F), maximum percent .....	2.0
Dielectric Strength <sup>1</sup> , 6 weeks at 204°C (400°F), kV peak (rms).....	42 (30)

<sup>1</sup>As per ASTM D 71 modified per ESM-486, all failures occurred at cable seal.

**Specification Writers: Please obtain a copy of the Dow Corning Sales Specification for this product and use it as a basis for your specifications. It may be obtained from any Dow Corning Sales Office, or from Dow Corning Customer Service in Midland, MI. Call (517) 496-6000.**

## HOW TO USE

*Molykote* G-5008 Dielectric Grease has been designed for use in automated dispensing equipment in which precise metering is required. This product can also be applied using a brush or a grease gun.

## SHIPPING LIMITATIONS

None.

## STORAGE AND SHELF LIFE

*Molykote* G-5008 Dielectric Grease can be stored for 60 months from date of manufacture at ambient temperatures in its original, closed container.

## PACKAGING

*Molykote* G-5008 Dielectric Grease is available in 18-kg (40-lb) pails and 181.4-kg (400-lb) drums.

**SAFE HANDLING INFORMATION**  
PRODUCT SAFETY INFORMATION  
REQUIRED FOR SAFE USE IS NOT  
INCLUDED IN THIS DOCUMENT.  
BEFORE HANDLING, READ PROD-  
UCT AND MATERIAL SAFETY DATA  
SHEETS AND CONTAINER LABELS  
FOR SAFE USE, PHYSICAL AND  
HEALTH HAZARD INFORMATION.  
THE MATERIAL SAFETY DATA  
SHEET IS AVAILABLE FROM YOUR  
DOW CORNING REPRESENTATIVE,  
OR DISTRIBUTOR, OR BY WRITING  
TO DOW CORNING CUSTOMER  
SERVICE, OR BY CALLING  
1-517-496-6000.

**LIMITED WARRANTY—  
PLEASE READ CAREFULLY**

Dow Corning believes that the  
information in this publication is an  
accurate description of the typical  
characteristics and/or uses of the  
product or products, but it is your  
responsibility to thoroughly test the  
product in your specific application  
to determine its performance, efficacy  
and safety. Suggestions of uses should  
not be taken as inducements to  
infringe any particular patent.

Unless Dow Corning provides you with  
a specific written warranty of fitness  
for a particular use, Dow Corning's  
sole warranty is that the product  
or products, as supplied, will meet  
Dow Corning's then current sales  
specifications. **DOW CORNING  
SPECIFICALLY DISCLAIMS ANY  
OTHER EXPRESS OR IMPLIED  
WARRANTY, INCLUDING THE  
WARRANTIES OF MERCHANT-  
ABILITY AND OF FITNESS FOR  
USE.** Your exclusive remedy and  
Dow Corning's sole liability for breach  
of warranty is limited to refund of the  
purchase price or replacement of any  
product shown to be other than as  
warranted, and Dow Corning expressly  
disclaims any liability for incidental or  
consequential damages.

*Dow Corning* and *Molykote* are registered trademarks  
of Dow Corning Corporation.  
©1998 Dow Corning Corporation.  
All rights reserved.

Printed in USA    AMPM1416/1198    Form No. 10-879-98